

R & A

120 Monarch Drive,
Streamwood, IL, 60107
847-414-2268
Chrypa75@yahoo.com

September 9, 2020

To Whom it May Concern:

The following product and coating technique will be applied for the Double Tree Project located at 7800 Normandale Blvd , Minneapolis MN.


REGAL® SELECT EXTERIOR PAINT – MOORLIFE® FLAT FINISH W105

Regal MoorLife is a premium quality, self priming, 100% acrylic exterior latex house paint in a popular flat finish. Our latest technological improvement, using 100% acrylic resin and proprietary alkyd technology, provides superior adhesion, especially to chalky substrates. This high solids formula delivers excellent durability, long lasting protection, and is suitable for a variety of exterior surfaces and can be applied at a wider temperature range

Following preparation steps will be applied. Surfaces must be clean and free of grease, wax, and mildew. Remove excessive chalk and loose or scaling paint. If previously coated with cementbase water paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (N318) prior to coating the surface. Caution: Refer to the (N318) Clean technical data and material safety data sheets for instructions on its proper use and handling. For metal surfaces, remove rust. Wipe down with paint thinner to remove surface oils if compliant with local requirements. All new masonry surfaces must be power washed or brushed thoroughly with stiff fiber bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds.

Following painting process will be implemented. Paint will be stirred thoroughly before and during use. Application of two coats. For best results, use of a Benjamin Moore® custom-blended nylon/polyester brush, Benjamin Moore® roller, or a similar product is recommended. Majority of the product will be sprayed. Following spray equipment will be used Graco Airless: Fluid Pressure — 1,500 to 2,500 PSI; Tip — .013 - .017 Orifice

Sincerely,



Robert Chrypa
R&A